

Werkstoff-Gruppe	AISI	W-stoff	DIN	BS	AFNOR	SS	U.N.E./I.H.A.	JIS	UNI	
5	W1	1.1545	C105W1	BW1A	Y 105	1880	F.5118	-	C38KU	
	420	1.4021	X42 Cr 13	420 S 37	Z 20 C 13	(2314)	F.3402	SUS 420 J1	X20Cr13	
	-	1.2108	90 CrSi 5	-	-	2092	F.5230	-	C100KU	
	L3	1.2210	115 CrV 3	BL 3	Y 100 C 6	(2140)	F.520 L	-	-	
	P20 + 1	1.2312	40 CrMnMoS 8 6	-	-	-	X210CrW12	-	-	
	O1	1.2510	100 MnCrW 4	BO1	8 Mo 8	2140	F.5220	-	95MnWCr5KU	
	6 F7	1.2767	X45 NiCrMo 6 7	En 30 B	-	-	-	-	-	
	-	-	31 NiCrMo 13 4	830 M 31	-	-	2534	F.1270	-	-
	4340	1.6582	34 CrNiMo 6	817 M 40	35 NCD 6	2541	F.1280	SNCM 447	35NiCrMo6KB	
	-	1.6746	32 NiCrMo 14 5	830 M 31	35 NCD 14	-	F.1260	-	-	
	S1	1.2542	45 WCrV 7	BS1	55 WC 20	2710	F.5241	-	45WCrV8KU	
	420	1.4021	X20 Cr 13	420 S 37	Z 20 C 13	2303	F.5261	SUS 420 J 1	X20Cr13	
	(420)	1.4028	X30 Cr 13	420 S 45	Z 30 C 13	(2304)	F.5263	(SUS 420 J 1)	X30Cr13/XG40Cr13	
	(420)	1.4031	X40 Cr 13	-	Z 40 C 14	(2304)	F.3404	(SUS 420 J 1)	X40Cr14	
	-	1.4923	X22 CrMoV 12 1	-	-	-	-	-	-	
	431	1.4057	X20 CrNi 17 2	431 S 29	Z 15 CN 16-02	2321	F.313	SUS 431	X16CrNi16	
440B	1.4112	X90 CrMoV 18	-	-	-	-	SUS 440 B	-		
6	P3	1.2080	X210 Cr 12	BD3	Z200 C 12	2710	F.5212	SKD 1	-	
	P20	1.2311	40 CrMnMo 7	-	-	-	F.5263	-	-	
	H13	1.2344	X40CrMoV 5 1	BH11	Z 38 CDV 5	2242	F.5318	SKD 61	X40CrMoV511KU	
	A2	1.2363	X100 CrMoV 5 1	BA2	Z 100 CDV 5	2260	F.5227	SKD 12	X100CrMoV51KU	
	D2	1.2379	X 155 CrMoV 12 1	BD2	Z 160 CDV 12	2310	F.5211	-	X155CrVMo121KU	
	D4 (D6)	1.2436	X210 CrW 12	BD6	Z 200 CD 12	2312	F.5213	SKD 2	X215CrW121KU	
	-	1.2713	55NiCrMoV 6	-	-	-	F.520.S	-	-	
	L6	1.2721	50 NiCr 13	-	55 NCV 6	2550	F.528	SKT 4	-	
	-	1.7321	20 MoCr 4	-	-	2625	F.1523	-	30CrMo4	
	M 2	1.3343	S6/5/2	BM2	Z 85 WDCW	2722	F.5603	SKH 9	HS6-5-2	
	M 35	1.3243	S6/5/2/5	-	6-5-2-5	2723	F.5613	SKH 55	HS6-5-5	
	M 7	1.3348	S2/9/2	-	-	2782	-	-	HS2-9-2	
	446	1.4749	X18 CrN 28	-	-	-	-	SUH 446	X16Cr26	
	422	1.4935	X20 CrMoWV 12 1	-	-	-	-	-	-	
	429	-	X10 CrNi 15	-	-	-	-	-	-	
	440C	1.4125	X105 CrMo 17	-	Z 100 CD 17	-	-	SUS 440 C	-	
7	A128 75	1.3401	G-X120 Mn 12	BW10	Z 120 M 12	2183	-	SCMnH 1	-	
8	304	1.4301	X5 CrNi 18 10	304 S 10	Z 5 CN 18-09	2333	-	SUS 304	X5CrNi1810	
	304H	1.4948	X6 CrNi 18 11	304 S 51	Z 5 CN 18-09	2333	-	SUS 304 H	-	
	303	1.4305	X10 CrNiS 18 9	303 S 31	Z 8 CNF 18-09	2346	-	SUS 303	X10CrNiS1809	
	304L	1.4306	X2 CrNi 18 10	304 S 11	Z 3 CN 19-11	2352	F.3504	SUS 304 L	X2CrNi1811	
	305	1.4312	X8 CrNi 18 12	305 S 19	-	-	F.3503	SUS 305	X8CrNi1910	
	302	-	X12 CrNi 18 9	302 S 31	Z 10 CN 18-09	2330	F.314	SUS 302	X10CrNi1809	
	301	1.4310	X12 CrNi 17 7	301 S 21	Z 11 CN 17-08	2331	-	SUS 301	X12CrNi1707	
	CF-8	1.4308	X6 CrNi 18 9	304 C 15	Z 6 CN 18-10M	2333	-	SCS 13	-	
9	321	1.4541	X6 CrNiTi 18 10	321 S 31	Z 6 CNT 18-10	2337	F.3523	SUS 321	X6CrNiTi1811	
	347	1.4550	X6 CrNiNb 1810	347 S 31	Z 6 CNNb 18-10	2338	-	SUS 347	X6CrNiNb1811	
	316	1.4436	X5 CrNiMo 17 13 3	316 S 33	Z 6 CND 19-12-03	2343	-	SUS 316	X5CrNiMo1713	
	316Ti	1.4571	X8 CrNiMoTi 17 12 2	320 S 31	-	-	-	-	X6CrNiTi1811	
	316	1.4401	X5 CrNiMo 17 12 2	316 S 31	Z 7 CND 17-11-02	2347	-	SUS 316	X5CrNiMo1712	
	316L	1.4404	X2 CrNiMo 17 13 2	316 S 11	Z 3 CND 17-12-02	2348	F.3533	SUS 316 L	X2CrNiMo1712	
	316Ti	1.4571	X6 CrNiMoTi 17 12 2	320 S 31	Z 6 CNDT 17-12-02	2350	F.3535	-	X6CrNiMoTi1712	
	316L	1.4435	X2 CrNiMo 18 14 3	316 S 13	Z 3 CND 18-14-03	2353	-	SUS 316 L	X2CrNiMo1713	
	317	(1.4449)	X5 CrNiMo 17 13	317 S 16	-	-	-	SUS 317	-	
	310S	1.4845	X12 CrNi 25 20	310 S 16	Z 12 CN 25-20	2361	-	SUH 310	X6CrNi2520	
	317L	1.4428	X2 CrNiMo 18 16 4	317 S 12	Z 2 CND 19-15-04	2367	-	SUS 317 L	X2CrNiMo1816	
	-	1.4418	X4 CrNiMo 16 5	-	Z 6 CND 16-04-01	2387	-	-	-	
	304LN	1.4311	X2 CrNiN 18 10	304 S 61	Z 2 CN 18-10 AZ	2371	-	SUS 304 LN	X2CrNiN1811	
309S	1.4833	X6 CrNi 22 13	309 S 13	Z 15 CN 24-13	-	-	SUS 309 S	X6CrNi2314		
CF-8M	1.4408	X6 CrNiMo 18 10	304 C 15	-	2343	-	SCS 14	-		
10	S44400	1.4521	X1CrMoTi 18 2	-	-	2326	-	SUS 444	-	
	202	1.4371	X3 CrMnNiN 18 8 7	284 S 16	Z 8 CMN 18-08-05	-	-	SUS 202	-	
	S30815	1.4893	X8 CrNiNb 11	-	-	2368	-	-	-	
	CA6-NM	1.4313	(G-)X4 CrNi 13 4	(425 C 11)	Z 4 CND 13-04 M	2385	-	SCS 5	(G)X6CrNi304	
	660	1.4980	X5 NiCrTi 25 15	-	Z 8 NCTV 25-15 B FF	2570	-	-	-	
	(S31726)	1.4439	X2 CrNiMoN 17 13 5	-	Z 3 CND 18-14-06 AZ	-	-	-	-	
	330	1.4864	X12 NiCrSi 16	NA 17	Z 12 NCS 35-16	-	-	SUH 330	-	
	309	-	X15 CrNi 23 13	309 S 24	Z 15 CNS 20-12	-	-	-	-	
310	1.4841	X15 CrNiSi 25 20	314 S 31	Z 15 CNS 25-20	-	-	-	X16CrNiSi2520		